

Report # K-418802-1502P34-R00

Samples Received:
Feb-24-15

Samples Tested:
Feb-24-15

Test Report

Kinectrics Inc., 800 Kipling Avenue, Unit 2
Toronto, Ontario, Canada
Tel: 416-207-6000, www.kinectrics.com



Tested for

ArcWear.com
Hugh Hoagland
ArcTesting@ArcWear.com
502-333-0510

Contact information for item tested:

UL LLC
12 Laboratory Drive
RTP, NC 27709
919-549-0937

Test item description

UL LLC,
Reference Number 4786793486, Mfg. Sarena Industries & Embroidery Mills,
Style Biyas, 8.4 oz/yd² 285 g/m² Twill,
80% FR Cotton 20% Nylon, Grey, AAD 9.2 oz/yd² 312 g/m²,
ArcWear# 1502P34

Reference Standard

ASTM F1959/F1959M-13
Standard Test Method for Determining the Arc Rating of Materials for Clothing

Test Parameters:

Test current: 8 kA

Number of samples analysed: 21

Arc Gap: 305 mm

Distance to Fabric: 305 mm

Incident Energy Range: 9 to 15 cal/cm²

Arc Rating, ATPV = 12 Cal/cm²
Heat Attenuation Factor, HAF = 77%

No variations to standard method noted.
Break-open Ebt not achieved or determined.
Samples tested as received, pre-test laundering as required by standard was arranged by client.

Summary

The Arc Rating of this material is intended for use as part of a flame resistant garment or system for workers exposed to electric arcs. The test result is applicable only to the test item as described; other fiber blends, weaves, finishing or dye may have different protection level. The test articles are tested as received; no test is done to validate the fiber content or composition. The Arc Rating was calculated based on the data obtained and analysed in accordance with the latest version of the applicable standards. The individual test sheets, graphs, photographs of the samples and video of every test are provided in digital format to the Client for review.

The arc testing performed to the above mentioned Standard is accredited by the Standards Council of Canada (SCC) to conform to the requirements of CAN-P-4E (ISO/IEC 17025:2005). Accreditation by the Standards Council of Canada (SCC) is a mark of competence and reliability recognized throughout the world.

Kinectrics Inc takes reasonable steps to ensure that all work performed shall meet the industry standards as set out in Kinectrics Inc.'s Quality Manual, and that all reports shall be reasonably free of errors, inaccuracies or omissions. KINETRICS INC. DOES NOT MAKE ANY WARRANTY OR REPRESENTATION WHATSOEVER, EXPRESS OR IMPLIED, WITH RESPECT TO THE MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE OF ANY INFORMATION CONTAINED IN THIS REPORT OR THE RESPECTIVE WORKS OR SERVICES SUPPLIED OR PERFORMED BY KINETRICS INC. Kinectrics Inc. does not accept any liability for any damages, either directly, consequentially or otherwise resulting from the use of this report.

Note: The test performed does not apply to electrical contact or electrical shock hazard.

©Kinectrics. Partial reproduction of this report is strictly prohibited without the express written consent of Kinectrics Inc.

Prepared by:

Approved by:

Andrew Haines
HCL Technologist
Ph: 416-207-6000

Claude Maurice
Test laboratory manager
Kinectrics Inc.

Note: For verification about results in this report, please forward copy of the report or inquiry to hcl@kinectrics.com

Date:
Feb-24-15

Determination of ATPV by performing logistic regression on the panel
burn response as indicated in Summary Table




Report #
K-418802-1502P34-R00

Test Performed in accordance with: ASTM F1959/F1959M-13

Fabric Description:

UL LLC,
Reference Number 4786793486, Mfg. Sarena Industries & Embroidery Mills,
Style Biyas, 8.4 oz/yd² 285 g/m² Twill,
80% FR Cotton 20% Nylon, Grey, AAD 9.2 oz/yd² 312 g/m²,
ArcWear# 1502P34




ATPV = 12 cal/cm²

Probability	Ei
5%	11.1
10%	11.4
20%	11.6
30%	11.8
40%	12.0
50%	12.1
60%	12.2
70%	12.4
80%	12.5
90%	12.8

(Note: ATPV is reported to nearest integer for ratings above 10 cal/cm²)

Total points analyzed = 21
Points above Stoll = 10
Points above mix zone = 9
Points below mix zone = 7
Pts within 20% = 17
Pts in mix zone = 5



HAF = 77 %

Confidence Intervals
95% CI = 75.3 , 78.7

Data pts

Best Fit

95% CI

95% CI pts

Date:
Feb-24-15

Summary of Measured Energy and Observations

Test Performed in accordance with : ASTM F1959/F1959M-13



Report #
K-418802-1502P34-R00

Fabric UL LLC,
Description: Reference Number 4786793486, Mfg. Sarena Industries & Embroidery Mills,
Style Biyas, 8.4 oz/yd² 285 g/m² Twill,
80% FR Cotton 20% Nylon, Grey, AAD 9.2 oz/yd² 312 g/m²,
ArcWear# 1502P34

	Test #	Panel	Test Current A	Cycles of 60Hz	Ei Cal/cm ²	SCD Cal/cm ²	HAF %	>Stoll Y/N	Break Open Y/N	Ablation Y/N	After Flame sec.	Omit Y/N	Comment
1	K-418802-1005	A	8223	11.2	8.6	-0.5	79.5	No	-	-	-	No	
2	K-418802-1005	B	8223	11.2	8.7	-0.3	78.7	No	-	-	-	No	
3	K-418802-1005	C	8223	11.2	10.4	-0.4	82.5	No	-	-	-	No	
4	K-418802-1006	A	8199	14.2	12.7	0.5	76.7	Yes	-	-	-	No	
5	K-418802-1006	B	8199	14.2	10.3	-0.2	77.6	No	-	-	-	No	
6	K-418802-1006	C	8199	14.2	12.5	0.1	80.0	Yes	-	-	-	No	
7	K-418802-1007	A	8204	15.2	11.5	-0.3	80.2	No	-	-	-	No	
8	K-418802-1007	B	8204	15.2	12.7	0.1	79.3	Yes	-	-	-	No	
9	K-418802-1007	C	8204	15.2	11.4	1.1	69.6	Yes	-	-	-	No	
10	K-418802-1008	A	8242	13.2	9.4	-0.3	78.6	No	-	-	-	No	
11	K-418802-1008	B	8242	13.2	12.2	-0.2	82.3	No	-	-	-	No	
12	K-418802-1008	C	8242	13.2	11.1	-0.3	81.8	No	-	-	-	No	
13	K-418802-1009	A	8197	16.2	13.0	1.5	70.7	Yes	-	-	-	No	
14	K-418802-1009	B	8197	16.2	11.8	-0.1	79.3	No	-	-	-	No	
15	K-418802-1009	C	8197	16.2	13.3	1.8	70.2	Yes	-	-	-	No	
16	K-418802-1010	A	8214	17.2	13.2	1.9	68.4	Yes	-	-	-	No	
17	K-418802-1010	B	8214	17.2	13.5	1.5	71.4	Yes	-	-	-	No	
18	K-418802-1010	C	8214	17.2	15.1	1.2	77.6	Yes	-	-	-	No	
19	K-418802-1011	A	8249	15.2	10.9	-0.1	78.7	No	-	-	-	No	
20	K-418802-1011	B	8249	15.2	14.3	0.4	79.8	Yes	-	-	-	No	
21	K-418802-1011	C	8249	15.2	12.0	-0.3	82.6	No	-	-	-	No	
22													
23													
24													
25													
26													
27													
28													
29													
30													
31													
32													
33													
34													
35													
36													
37													
38													
39													